

FOUNDATION Geotextiles

256 Paper Lane, Clarkesville, GA 30523, phone 706/839-6632, fax 706/839-6634

Technical Data Sheet

FGSH80

<i>Property</i>	<i>Test Procedure</i>	UNIT	MARV
Grab Tensile Strength	ASTM D-4632	Lbs/in	250 x 180
Trapezoidal Tear	ASTM D-4533	Lbs	105 x 80
Puncture	ASTM D-6241	Lbs	100
Shade		%	80
Weight	ASTM D-5261	Oz/sq-yrd	5.0

MARV: Minimum average roll value

Note: Minimum average roll values represent a 97.5% confidence level, calculated as the mean minus two standard deviations.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. Foundation Geotextiles assumes no liability in connection with the use of this information.