

FOUNDATION Geotextiles

256 Paper Lane, Clarkesville, GA 30523, phone 706/839-6632, fax 706/839-6634

Technical Data Sheet

FGSH47

<i>Property</i>	<i>Test Procedure</i>	UNIT	MARV
Grab Tensile Strength	ASTM D-4632	Lbs/in	120 x 85
Trapezoidal Tear	ASTM D-4533	Lbs	60 X 45
Puncture	ASTM D-6241	Lbs	35
Shade		%	47
Weight	ASTM D-5261	Oz/sq-yrd	2.5

MARV: Minimum average roll value

Note: Minimum average roll values represent a 97.5% confidence level, calculated as the mean minus two standard deviations

This information is provided for reference purposes only and is not intended as a warranty or guarantee. Foundation Geotextiles assumes no liability in connection with the use of this information.